

## PE Foam Tubes



<b>Colour</b>		Charcoal
<b>Compression Set (Room temp 22hr)</b>	ASTM D395-03	27
<b>Tensile Strength</b>	ASTM D412-06a	2.8 kgf/cm <sup>3</sup>
<b>Elongation</b>	ASTM D412-06a	76%
<b>Compressive Strength (kgf/cm<sup>3</sup> x 10% Strain)</b>	ASTMD1621-04a	5.1
<b>Surface</b>		Plain both sides
<b>Density</b>	ASTM C303-07	27g/cm <sup>3</sup>
<b>Water Absorption (%) 23°C, 24hr)</b>	ASTM C272-01	3.9%